



## Specification Guide for Copper Azole Treated Wood End Uses

Wood Treated Right™		AWPA Standards		Preservative Retention
		U 1	C	(Lbs. per cubic foot)
		UCS	Commodity	CA -B
AGRICULTURE, FARM USE	Round poles and posts as structural members	4B	C4, C16	.31
	Sawn poles and posts as structural members	4B	C2, C16	.31
	Posts, Fence			
	Round, half & quarter round	4A	C5, C16	.21
	Sawn four sides	4A	C2, C16	.21
	Lumber, in soil contact	4A	C2, C16	.21
	Lumber, not in soil contact	3B	C2, C16	.10
	Plywood, in soil contact	4A	C9, C16	.21
	Plywood, not in soil contact	3B	C9, C16	.10
	Grape stakes, sawn	4A	C2, C16	.21
BUILDING CONSTRUCTION MATERIAL	Floor plate	2	C2, C15	.10
	Flooring, residential			
	Damp environment	2	C2	.10
	Dry environment	1	C2	.10
	Framing, interior	1, 2	C2, C15	.10
	Lumber			
	Interior, above ground	1, 2	C2, C15	.10
	Exterior, above ground	3B	C2, C15	.10
	Ground contact and fresh water use	4A	C2	.21
	Permanent Wood Foundation			
	Lumber & Plywood	4B	C22	.31
	Plywood			
	Sub-floor, damp above ground	2	C9, C15	.10
	Exterior, above ground	3B	C9, C15	.10
	Ground contact and fresh water use	4A	C9	.21
	Poles, building			
	Round	4B	C4, C23	.31
Sawn	4B	C2, C15, C24	.31	
DECKS	Above ground: Decking, joists, rails, steps	3B	C2, C15	.10
	Sapwood species: Decking, specialties		N ER-669	.08
	Ground contact: Posts	4A	C2, C15	.21
FENCES	Pickets, slats, trim	3A, 3B	C2, C15	.10
	Posts, sawn	4A	C2, C15	.21
HIGHWAY MATERIAL	Lumber and timbers for bridges, structural members, decking, cribbing, & culverts			
		4B	C2, C14	.31
	Structural lumber and timbers:			
	Posts: Round, half-round, quarter round	4A	C5, C14	.21
	Posts: Sawn	4A	C2, C14	.21
	Handrails and guardrails	3B	C2, C14	.10
	Posts, guardrail			
Round	4A	C5, C14	.25	
Sawn	4A	C2, C14	.25	

Arch Treatment Technologies, Inc.  
1955 Lake Park Drive, Suite 250

Smyrna, GA 30080

[www.wolmanizedwood.com](http://www.wolmanizedwood.com) 1-866-789-4567